

## Carbinol Silicone Oil For Personal Care RH-C230

**INCI:** Bis-Hydroxyethoxypropyl dimethicone

### Features:

RH-C230 silicone oil is carbinol functional silicone fluid. The product has excellent skin affinity, unique compatibility, wettability, moisture retention and fragrance retention; it has a good dispersion and suspension effect for color powder, which can improve the stability of color makeup formula and the SPF value of sunscreen nursing formula; at the same time, it has a good affinity and moisturizing effect on lips, and has good brightness.

### Parameter:

Item	Standard
INCL Name	Bis-Hydroxyethoxypropyl dimethicone
Appearance	Colorless to yellowish, transparent to slightly turbid liquid
Viscosity(25°C,mm <sup>2</sup> /s)	40~60
Refractive Index(25°C)	1.40~1.43
Density(25°C)	0.96~1.00

### Application:

This product is suitable for cosmetics, sunscreen, facial and body products, antiperspirant deodorant products and hair scale care products. The recommended dosage is 0.1 ~ 20%.

**Zhejiang Runhe Chemical New Materials Co., Ltd**

Room 1906, Guangli Mansion, No. 136 Qingchun Road, Hangzhou, Zhejiang, China

Tel: 86-571-85092338 Fax: 86-571-87246635

Website: [www.chinarunhe.com](http://www.chinarunhe.com) [www.runhesilicone.com](http://www.runhesilicone.com)

Email: [runhe@chinarunhe.com](mailto:runhe@chinarunhe.com)



浙江润禾化工新材料有限公司  
Zhejiang Runhe Chemical New Materials Co., Ltd

---

**Package:**

20/200L steel drum OR other required package.

**Storage & Transpotation:**

The product should be stored in a cool and dry place once sealed, avoid contact with acid and alkali, and away from fire source. The effective storage period is 12 months.

**DISCLAIMER**

The technical parameters provided in this paper are all typical values for reference only. They are not regarded as product acceptance standards and are subject to change without notice. Due to the difference of use conditions, we can not guarantee the effect and applicability of the product under all circumstances, and we will not be liable for any direct, indirect or accidental losses arising therefrom. Users shall conduct relevant tests or consult our technical personnel before using the product.